

Clinical Recipe for Durable Dental Bonding: Why and How?

Bart van Meerbeek^a / Kumiko Yoshihar^b

IAAD WORKING INSTRUCTIONS

Current dental adhesive technology involves either an etch-and-rinse or self-etching approach.⁸ Evidence of clinical durability exists for both approaches, albeit depending on the specific brand.^{4,5} Today, enamel still requires phosphoric-acid etching and thus an etch-and-rinse approach to obtain a durable bond. The adhesive-enamel bond seals the cavity and even protects the more vulnerable bond to adjacent dentin.³ Although functional monomers in self-etching adhesives are designed to chemically interact with hydroxyapatite (HAp), the structure, size, and orientation of enamel HAp crystals appear to provide insufficient chemical bonding sites to achieve durable bonding to enamel. As a rule, the micro-mechanical interlocking provided by the etch-and-rinse step remains necessary. For dentin, phosphoric acid may be less preferable, as adhesives generally cannot envelop the exposed collagen tightly enough to make the relatively thick hybrid layer resistant to hydrolytic and enzymatic degradation processes.² Ethanol wet bonding⁶ and biomimetic repair⁷ by remineralization of etch-and-rinse hybrid layers have proven to be effective. However, these techniques are rather time consuming, which makes their applicability questionable for routine clinical practice. Moreover, the use of MMP inhibitors applied separately or mixed with the primer/adhesive appeared to retard rather than prevent bond degradation.^{1,6} Another strategy employed in the attempt to improve bond durability to dentin involves chemical interaction of functional monomers with HAp following a “mild” self-etching approach.⁹ Among the current functional monomers investigated, the phosphate monomers 10-MDP and more recently also MF8P were documented to bond durably to hydroxyapatite.^{9,12} In addition, correlative chemical (XRD, NMR) and high-resolution (TEM) structural interfacial analysis revealed that both monomers self-assemble into nanolayers, consisting of two monomer molecules joined by stable monomer-Ca salt formation.^{10,11} The stable bond formed to HAp along with interfacial nanolayering is thought to be the basis for the more biodegradation-resistant adhesive interface. Strategies to intensify nanolayering need to be explored further.

^a Professor, KU Leuven BIOMAT, Department of Oral Health Sciences, KU Leuven (University of Leuven) and Dentistry, University Hospitals Leuven, Leuven, Belgium. e-mail: bart.vanmeerbeek@med.kuleuven.be

^b PhD Student, KU Leuven BIOMAT, Department of Oral Health Sciences, KU Leuven (University of Leuven) and Dentistry, University Hospitals Leuven, Leuven, Belgium.

Do	Why
Selectively etch enamel for 15 s minimum with phosphoric acid and rinse.	Enamel requires microretention; attempt to avoid etching dentin, but realize that this is not crucial.
Rub a 10-MDP-based self-etching primer for 15 s minimum onto the etched enamel and unetched dentin, and air thin until the primer film no longer moves.	10-MDP ionically bonds to HAp and self-assembles into nanolayers.
Apply a solvent-free adhesive resin, air thin, and light cure separately prior to the first layer of composite.	To seal and stabilize the adhesive interface; in case of indirect bonding, employ the ‘immediate sealing’ (multi-visit treatment) approach or air thin (no pooling) the adhesive prior to light curing (one-visit treatment) in order not to impair the restoration fit.

REFERENCES

- De Munck J, Van den Steen PE, Mine A, Van Landuyt KL, Poitevin A, Opdenakker G, Van Meerbeek B. Inhibition of enzymatic degradation of adhesive-dentin interfaces. *J Dent Res* 2009;88:1101-1116.
- De Munck J, Van Landuyt K, Peumans M, Poitevin A, Lambrechts P, Braem M, Van Meerbeek B. A critical review of the durability of adhesion to tooth tissue: methods and results. *J Dent Res* 2005;84:118-132.
- De Munck J, Van Meerbeek B, Yoshida Y, Inoue S, Vargas M, Suzuki K, Lambrechts P, Vanherle G. Four-year water degradation of total-etch adhesives bonded to dentin. *J Dent Res* 2003;82:136-140.
- Peumans M, De Munck J, Van Landuyt KL, Poitevin A, Lambrechts P, Van Meerbeek B. A 13-year clinical evaluation of two three-step etch-and-rinse adhesives in non-carious class-V lesions. *Clin Oral Investig* 2012;16:129-137.
- Peumans M, De Munck J, Van Landuyt KL, Poitevin A, Lambrechts P, Van Meerbeek B. Eight-year clinical evaluation of a 2-step self-etch adhesive with and without selective enamel etching. *Dent Mater* 2010;26:1176-1184.
- Sadek FT, Braga RR, Muench A, Liu Y, Pashley DH, Tay FR. Ethanol wet-bonding challenges current anti-degradation strategy. *J Dent Res* 2010;89:1499-1504.
- Tay FR, Pashley DH. Guided tissue remineralisation of partially demineralised human dentine. *Biomaterials* 2008;29:1127-1137.
- Van Meerbeek B, De Munck J, Yoshida Y, Inoue S, Vargas M, Vijay P, Van Landuyt K, Lambrechts P, Vanherle G. Buonocore memorial lecture. Adhesion to enamel and dentin: current status and future challenges. *Oper Dent* 2003;28:215-235.
- Yoshida Y, Nagakane K, Fukuda R, Nakayama Y, Okazaki M, Shintani H, Inoue S, Tagawa Y, Suzuki K, De Munck J, Van Meerbeek B. Comparative study on adhesive performance of functional monomers. *J Dent Res* 2004;83:454-458.
- Yoshida Y, Yoshihara K, Nagaoka N, Hayakawa S, Torii Y, Ogawa T, Osaka A, Van Meerbeek B. Self-assembled nano-layering at the adhesive interface. *J Dent Res* 2012;91:376-381.
- Yoshihara K, Yoshida Y, Hayakawa S, Nagaoka N, Irie M, Ogawa T, Van Landuyt KL, Osaka A, Suzuki K, Minagi S, Van Meerbeek B. Nanolayering of phosphoric acid ester monomer on enamel and dentin. *Acta Biomater* 2011;7:3187-195.
- Yoshihara K, Yoshida Y, Hayakawa S, Nagaoka N, Kamenoue S, Okihara T, Ogawa T, Nakamura M, Osaka A, Van Meerbeek B. Novel fluoro-carbon functional monomer for dental bonding. *J Dent Res* 2014;93:189-194.

Copyright of Journal of Adhesive Dentistry is the property of Quintessence Publishing Company Inc. and its content may not be copied or emailed to multiple sites or posted to a listserv without the copyright holder's express written permission. However, users may print, download, or email articles for individual use.